



Application	v <sub>c</sub> factor	f <sub>x</sub> factor	Feed width (ae)	Feed depth (ap)
Slotting	1	1 (0.7 for a <sub>p</sub> = 2xd)	1xd	0.5 up to 1xd
Roughing	1	1 (0.7 for a <sub>p</sub> = 2xd)	0.4 up to 0.9xd	0.5 up to 1xd
Finishing	1	1	0.01 up to 0.1xd	1 up to 2xd
HPC-roughing	1.3	1.5	0.15 up to 0.4xd	1 up to 2xd
HSC-roughing	1.5	2	0.05 up to 0.15xd	1 up to 2xd

Material	Hardness	Recommended GH 100 type	Type of application	cut Vc	fz (mm/z) with nom. Ø							
					3	6	8	10	12	16	20	25
Structural + free-cutting steels, unalloyed heat-treatable + case hardened steels 1.0035 S185, 1.0486 P275N, 1.0345 P235GH, 1.0050, 1.0070, 1.8937 1.0718 11SMnPb30, 1.0736 11SMn37 1.0402 C22, 1.1178 C30E 1.0503 C45, 1.1191 C30E 1.0301 C10, 1.1121 C10E 1.1750 C75W, 1.2076 102Cr6, 1.2307 29CrMoV9	up to 850 N/mm <sup>2</sup>	U (3-Flt.)	Slotting	120	0.012	0.024	0.041	0.045	0.054	0.070	0.090	0.110
		U (3-Flt.)	Roughing	140	0.014	0.028	0.037	0.052	0.062	0.080	0.100	0.130
		U (6-/8-Flt.)	Finishing	240	0.013	0.026	0.035	0.050	0.059	0.080	0.100	0.120
Free-cutting steels, unalloyed case hardened steels, nitriding steels 1.0727 46 S20, 1.0728 60 S20, 1.0757 46SPb20 1.0601 C60, 1.1221 C60E 1.7043 38Cr4 1.5752 15NiCr13, 1.7131 16MnCr5, 1.7264 20CrMo5 1.8504 34CrAl6 1.8519 31CrMoV9, 1.8550 34CrAlNi7	850-1,200 N/mm <sup>2</sup>	U (3-Flt.)	Slotting	105	0.012	0.024	0.041	0.045	0.054	0.070	0.090	0.110
		U (3-Flt.)	Roughing	130	0.014	0.028	0.037	0.052	0.062	0.080	0.100	0.130
		U (6-/8-Flt.)	Finishing	210	0.013	0.026	0.035	0.050	0.059	0.080	0.100	0.120
Alloyed heat-treatable, tool and high speed steels 1.5131 50MnSi4, 1.7003 38Cr2, 1.7030 28Cr4 1.5710 36NiCr6, 1.7035 41Cr4, 1.7225 42CrMo4 1.2080 X210Cr12, 1.2083 X42Cr13, 1.2419 105WCr6, 1.2379 X155CrVMo12-1 1.3243 S 6-5-2, 1.3343 S 6-5-2, 1.3344 S 6-5-3 Spring steel = 1.5026 55Si7, 1.7176 55Cr3, 1.8159 51CrV4	850-1,400 N/mm <sup>2</sup>	U (3-Flt.)	Slotting	90	0.011	0.023	0.030	0.042	0.050	0.070	0.080	0.110
		U (3-Flt.)	Roughing	110	0.013	0.026	0.035	0.048	0.058	0.080	0.100	0.120
		U (6-/8-Flt.)	Finishing	180	0.013	0.025	0.033	0.046	0.055	0.070	0.090	0.120
Hardened steel Tool steel, heat-treatable steel, spring steel, high-speed steel, case hardened steel, etc. Z.B.: 1.2344 X40CrMoV5-1; 1.2767 X45NiCrMo4; 1.2379 X155CrVMo12-1; 1.2080 X210Cr12 1.3343 S 6-5-2	up to 54 HRC	U (3-Flt.)	Slotting	50	0.010	0.019	0.026	0.035	0.042	0.060	0.070	0.090
		H (6-/8-Flt.)*	Roughing	100	0.024	0.048	0.064	0.088	0.105	0.140	0.180	0.220
		H (6-/8-Flt.)	Finishing	110	0.010	0.019	0.026	0.035	0.042	0.060	0.070	0.090
	54-60 HRC		Finishing	70	0.019	0.038	0.050	0.070	0.084	0.110	0.140	0.180
		H (6-/8-Flt.)		80	0.007	0.014	0.018	0.025	0.030	0.040	0.050	0.060
Stainless steel 1.4104 X14CrMoS17, 1.4105 X6CrMoS17, 1.4305 X10CrNiS18-9 USA = 303, 410, 420F, 430, 430F	up to 750 N/mm <sup>2</sup>	U (3-Flt.)	Slotting	80	0.011	0.023	0.030	0.042	0.050	0.070	0.050	0.110
		U (3-Flt.)	Roughing	100	0.013	0.026	0.035	0.048	0.058	0.080	0.100	0.120
		U (6-/8-Flt.)	Finishing	160	0.013	0.025	0.033	0.046	0.055	0.070	0.090	0.120
Stainless steel 1.4301X5CrNi18-10, 1.4303 X5CrNi18-12 1.4310 XCrNi18-8 USA = 304, 304L, 420	750-850 N/mm <sup>2</sup>	U (3-Flt.)	Slotting	55	0.011	0.021	0.028	0.038	0.046	0.060	0.080	0.100
		U (3-Flt.)	Roughing	70	0.012	0.024	0.032	0.044	0.052	0.070	0.090	0.110
		U (6-/8-Flt.)	Finishing	110	0.012	0.023	0.031	0.042	0.050	0.070	0.080	0.100
Stainless steel 1.4438 X2CrNiMo18-15-4, 1.4404 X2CrNiMo17-12-2, 1.4571 X6CrNiTi18-10 USA = 310, 316, 316B, 316L, 317	above 850 N/mm <sup>2</sup>	U (3-Flt.)	Slotting	40	0.010	0.020	0.026	0.035	0.042	0.050	0.070	0.090
		U (3-Flt.)	Roughing	50	0.012	0.024	0.032	0.042	0.050	0.070	0.080	0.110
		U (6-/8-Flt.)	Finishing	80	0.010	0.020	0.026	0.035	0.042	0.060	0.070	0.090
Special alloys (nickel based "Ni") Nimonic, Inconel, Monel, Hastelloy	up to 1,300 N/mm <sup>2</sup>	U (3-Flt.)	Slotting	40	0.010	0.020	0.026	0.038	0.046	0.060	0.080	0.100
		U (3-Flt.)	Roughing	50	0.012	0.024	0.032	0.046	0.055	0.070	0.090	0.110
		U (6-/8-Flt.)	Finishing	80	0.011	0.022	0.029	0.042	0.050	0.070	0.080	0.100
Titanium alloys ("Ti") 3.7024 Ti99,5, 3.7114 TiAl5Sn2,5, 3.7124 TiCu2 3.7154 TiAl6Zr5, 3.7164 TiAl6V4, 3.7184 TiAl4Mo4Sn2,5	up to 1,300 N/mm <sup>2</sup>	U (3-Flt.)	Slotting	20	0.008	0.015	0.020	0.030	0.036	0.050	0.060	0.080
		U (3-Flt.)	Roughing	30	0.009	0.018	0.024	0.036	0.043	0.060	0.070	0.090
		U (6-/8-Flt.)	Finishing	40	0.008	0.015	0.020	0.030	0.036	0.050	0.060	0.080
Cast iron, grey cast iron, spheroidal graphite and malleable cast iron 0.6010 EN-GL100 (GG10), 0.6020 EN-GJL-200 (GG20), 0.7050 EN-GJS-500-7 (GGG50), 0.8535 EN-GJMW-350-4 (GTW35)	up to 240 HB 30	U (3-Flt.)	Slotting	105	0.012	0.024	0.032	0.045	0.054	0.070	0.090	0.110
		U (3-Flt.)	Roughing	130	0.014	0.028	0.037	0.052	0.062	0.080	0.100	0.130
		U (6-/8-Flt.)	Finishing	210	0.013	0.026	0.035	0.050	0.059	0.080	0.100	0.120
Cast iron, grey cast iron, spheroidal graphite and malleable cast iron 0.6025 EN-GL250 (GG25), 0.6035 EN-GJL-350 (GG35), 0.7070 EN-GJS-700-2 (GGG70), 0.8170 EN-GJMB-700-2 (GTS70)	above 240 HB 30	U (3-Flt.)	Slotting	90	0.011	0.023	0.030	0.042	0.050	0.070	0.080	0.110
		U (3-Flt.)	Roughing	110	0.013	0.026	0.035	0.048	0.058	0.080	0.100	0.120
		U (6-/8-Flt.)	Finishing	180	0.013	0.025	0.033	0.046	0.055	0.070	0.090	0.120
Aluminum, Al-wrought alloys, Al-alloys 3.0255 Al99,5, 3.2315 AlMgSi1, 3.3515 AlMg1 3.0615 AlMgSiPb, 3.1325 AlCuMg1, 3.3245 AlMg3Si, 3.4365 AlZnMgCu1,5	up to 3% Si	A (3-Flt.)	Slotting	300	0.015	0.030	0.040	0.055	0.066	0.090	0.110	0.140
		A (3-Flt.)	Roughing	400	0.017	0.035	0.046	0.063	0.076	0.100	0.130	0.160
		A (3-Flt.)	Finishing	600	0.017	0.033	0.044	0.061	0.073	0.100	0.120	0.150
Aluminum-cast alloys 3.2131 G-AlSi5Cu1, 3.2153 G-AlSi7Cu3, 3.2573 G-AlSi9 3.2581 G-AlSi12, 3.2583 G-AlSi12Cu, - G-AlSi12CuNiMg	above 3% Si	A (3-Flt.)	Slotting	180	0.014	0.027	0.036	0.050	0.060	0.080	0.100	0.130
		A (3-Flt.)	Roughing	300	0.016	0.031	0.041	0.058	0.069	0.090	0.120	0.140
		U (6-/8-Flt.)	Finishing	360	0.015	0.030	0.040	0.055	0.066	0.090	0.110	0.140
Magnesium-alloys MgMn2, G-MgAl8Zn1, G-MgAl6Zn3	—	A (3-Flt.)	Slotting	150	0.013	0.025	0.034	0.045	0.054	0.070	0.090	0.110
		A (3-Flt.)	Roughing	180	0.014	0.029	0.039	0.052	0.062	0.080	0.100	0.130
		A (3-Flt.)	Finishing	300	0.014	0.028	0.037	0.050	0.059	0.080	0.100	0.120
Non-ferrous metals (copper, short- or long-chipping brass or bronze) 2.0070 SE-Cu, 2.1020 CuSn6, 2.1096 G-CuSn5ZnPb 2.0380 CuZn39Pb2, 2.0401 CuZn39Pb3, 2.0410 CuZn43Pb2 2.0250 CuZn20, 2.0280 CuZn33, 2.0332 CuZn37Pb0,5 2.1090 CuSn7ZnPb, 2.1170 CuPb5Sn5, 2.1176 CuPb10Sn 2.0916 CuAl5, 2.0960 CuAl9Mn, 2.1050 CuSn10	up to 850 N/mm <sup>2</sup>	A (3-Flt.)	Slotting	200	0.014	0.027	0.036	0.050	0.060	0.080	0.100	0.130
		A (3-Flt.)	Roughing	230	0.016	0.031	0.041	0.058	0.069	0.090	0.120	0.140
		U (6-/8-Flt.)	Finishing	400	0.015	0.030	0.040	0.055	0.066	0.090	0.110	0.140

\* trochoid milling strategy

All recommendations are valid for coated tools. For bright milling cutters please vc - 40% and fz - 25%