

CODE LISTED
ICC-ES ESR-2582
CATEGORY 1
Cracked & Uncracked Concrete



AC100+Gold[®]

Adhesive Anchoring System

FASTENAL[®]

Powers[®]
FASTENING INNOVATIONS

AC100+Gold®

Vinylester Injection Adhesive Anchoring System



PRODUCT DESCRIPTION

The AC100+Gold is a two-component vinylester adhesive anchoring system. The system includes injection adhesive in plastic cartridges, mixing nozzles, dispensing tools and hole cleaning equipment. The AC100+Gold is designed for bonding threaded rod and reinforcing bar elements into drilled holes in concrete and masonry base materials.

GENERAL APPLICATIONS AND USES

- Bonding threaded rod and reinforcing bar into hardened concrete and masonry
- Evaluated for use in dry and water-saturated concrete including water filled holes
- Suitable to resist loads in cracked or uncracked concrete base materials for cases where anchor design theory and criteria applies
- Can be installed in a wide range of base material temperatures
- Qualified for seismic and wind loading (see ESR-2582)

FEATURES AND BENEFITS

- Designed for use with threaded rod and reinforcing bar hardware elements
- Consistent performance in low and high strength concrete (2,500 to 8,500 psi)
- Evaluated and recognized for freeze/thaw performance
- Evaluated and recognized for a range of embedments in interior and exterior applications
- Versatile low odor formula with quick cure time
- Evaluated and recognized for long term and short term loading (see performance tables)
- Mixing nozzles proportion adhesive and provide simple delivery method into drilled holes
- Cartridge design allows for multiple uses using extra mixing nozzles

TESTING AND EVALUATION

Tested and evaluated by an accredited independent laboratory in accordance with ICC-ES AC308 criteria and ASTM E 1512 for anchoring in uncracked concrete, including but not limited to the following:

- Reliability testing for freeze/thaw conditions
- Reliability testing for sensitivity to hole cleaning, mixing effort and installation direction
- Reliability testing for sustained loads, i.e. creep resistance (see applicable long-term and short-term temperature ranges)
- Service condition testing at elevated and decreased temperatures
- Service condition testing in low and high strength concrete
- Service condition testing for resistance to alkalinity and sulfur exposure

APPROVALS AND LISTINGS

- International Code Council, Evaluation Service (ICC-ES) ESR-2582 (Including FBC Supplement)
- Code compliant with the 2009 IBC, 2009 IRC, 2006 IBC, 2006 IRC, 2003 IBC and 2003 IRC
 - Tested in accordance with ASTM E 488 and ICC-ES AC308 for use in structural concrete with ACI 318 Appendix D (Strength Design) and as amended by provisions of ICC-ES AC308 Annex A, Section 3.3 (www.icc-es.org)
 - Compliant with NSF/ANSI Standard 61 for drinking water system components – health effects; minimum requirements for materials in contact with potable water and water treatment
 - Conforms to requirements of ASTM C 881, Types I, II, IV and V, Grade 3, Classes A & B (meets Type III with exception of elongation)
 - Department of Transportation listings – see www.powers.com or contact transportation agency

GUIDE SPECIFICATIONS

CSI Divisions: 03151-Concrete Anchoring, 04081 Masonry Anchorage and 05090-Metal Fastenings. Adhesive anchoring system shall be AC100+Gold as supplied by Powers Fasteners, Inc., Brewster, NY. Anchors shall be installed in accordance with published instructions and requirements of the Authority Having Jurisdiction.

PACKAGING

Coaxial Cartridge

5 fl. oz. (150 ml or 9.2 in³)
10 fl. oz. (280 ml or 17.1 in³)

Dual (Side-by-Side) Cartridge

8 fl. oz. (235 ml or 14.3 in³)
12 fl. oz. (345 ml or 21.0 in³)
28 fl. oz. (825 ml or 50.3 in³)

STORAGE LIFE & CONDITIONS

Fifteen months in a dry, dark environment with temperature ranging from 32°F and 86°F (-0°C to 30°C)

ANCHOR SIZE RANGE (TYP.)

3/8" to 1-1/4" diameter threaded rod
No. 3 to No. 10 reinforcing bar (rebar)

SUITABLE BASE MATERIALS


Normal-weight concrete
Grouted concrete masonry
Hollow concrete masonry
Brick masonry



AC100+Gold®

CRACKED CONCRETE BOND STRENGTH COMPARISON

Characteristic Bond Strength Comparison for Acrylic Adhesive Anchoring Systems Installed into Cracked Normal-Weight Concrete with 1/2-inch Threaded Rod^{1,2}



1. All data is based on independent ICC-ES evaluation report data available at www.ic-es.org.

2. Characteristic bond strength based on ICC-ES AC308 Temperature Range A: Maximum long-term temperature = 75°F (24°C), maximum short-term temperature = 104°F (40°C)

ICC-ES Code Listed for Installation Into Concrete

Powers AC100+Gold	See ESR-2582
Hilti HIT-HY 150 MAX SD	See ESR-3013
ITW Epcon S7	See ESR-2308
Simpson AT-XP	No ICC-ES Report for Concrete

Hilti is a registered trademark of Hilti Corp.
ITW is a registered trademark of Illinois Tool Works, Inc.
Simpson is a registered trademark of the Simpson Strong-Tie Company, Inc.

AC100+Gold®

INSTALLATION SPECIFICATIONS

Installation Specifications for Threaded Rod and Reinforcing Bar (Solid Base Materials)

Dimension/Property		Notation	Units	Nominal								
Threaded rod		-	-	3/8"	1/2"	5/8"	3/4"	7/8"	1"	-	1-1/4"	-
Reinforcing bar		-	-	#3	#4	#5	#6	#7	#8	#9	-	#10
Nominal anchor diameter		d	in. (mm)	0.375 (9.5)	0.500 (12.7)	0.625 (15.9)	0.750 (19.1)	0.875 (22.2)	1.000 (25.4)	1.125 (28.6)	1.250 (31.8)	1.250 (31.8)
Nominal diameter of drilled hole		$d_o, (d_{bit})$	in.	7/16 ANSI	9/16 ANSI	11/16 ANSI	7/8 ANSI	1 ANSI	1-1/8 ANSI	1-3/8 ANSI	1-3/8 ANSI	1-1/2 ANSI
Minimum embedment ¹		$h_{ef,min}$	in. (mm)	2-3/8 (61)	2-3/4 (70)	3-1/8 (79)	3-1/2 (89)	3-1/2 (89)	4 (102)	4-1/2 (114)	5 (127)	5 (127)
Maximum embedment ¹		$h_{ef,max}$	in. (mm)	4-1/2 (114)	6 (153)	7-1/2 (191)	9 (229)	10-1/2 (267)	12 (305)	13-1/2 (343)	15 (381)	15 (381)
Minimum concrete member thickness ¹		h_{min}	in. (mm)	$h_{ef} + 1-1/4$ ($h_{ef} + 30$)			$h_{ef} + 2d_o$					
Minimum spacing distance ¹		s_{min}	in. (mm)	1-7/8 (48)	2-1/2 (62)	3-1/8 (80)	3-3/4 (95)	4-3/8 (111)	5 (127)	5-5/8 (143)	6-1/4 (159)	6-1/4 (159)
Minimum edge distance ¹		c_{min}	in. (mm)	1-7/8 (48)	2-1/2 (64)	3-1/8 (80)	3-3/4 (95)	4-3/8 (111)	5 (127)	5-5/8 (143)	6-1/4 (159)	6-1/4 (159)
Maximum torque (only possible after full cure time of adhesive)	A307 Grade C or F1554 carbon steel rod	T_{max}	ft.-lb. (N-m)	10 (13)	25 (34)	50 (68)	90 (122)	125 (169)	165 (224)	-	280 (379)	-
	F593 Condition CW stainless steel rod or ASTM A193, Grade B7 carbon steel rod	T_{max}	ft.-lb. (N-m)	16 (22)	33 (45)	60 (81)	105 (142)	125 (169)	165 (224)	-	280 (379)	-

1. For use with the design provisions of ACI 318 Appendix D and ICC-ES AC308 Annex A Section 3.3 and ESR-2582.


Installation Specifications for Threaded Rod (Hollow Base Material)

Dimension/Property	Notation	Units	Nominal Anchor Size	
			3/8"	1/2"
Nominal anchor diameter	d	in. (mm)	0.375 (9.5)	0.500 (12.7)
Nominal stainless steel tube size	-	in.	3/8	1/2
Nominal diameter of drilled hole	$d_o, (d_{bit})$	in.	1/2 ANSI	5/8 ANSI
Maximum torque (only possible after full cure time of adhesive)	T_{max}	in. (mm)	4-1/2 (114)	6 (153)

Threaded Rod and Deformed Reinforcing Bar Material Properties

Steel Description (General)	Steel Specification (ASTM)	Nominal Anchor Size (inch)	Minimum Yield Strength, f_y (ksi)	Minimum Ultimate Strength, f_u (ksi)
Carbon rod	A 36 or F1554 Grade 36	3/8 through 1-1/4	36.0	58.0
Stainless rod (Alloy 304 / 316)	F 593, Condition CW	3/8 through 5/8	65.0	100.0
		3/8 through 1-1/4	45.0	85.0
High Strength Carbon rod	A 193 Grade B7	3/8 through 1-1/4	105.0	125.0
Grade 60 reinforcing bar	A 615, A 706, A 767, or A 996	3/8 through 1-1/4 (#3 through #10)	60.0	90.0
Grade 40 reinforcing bar	A 615 or A 767	3/8 through 1-1/4 (#3 through #6)	40.0	60.0

Detail of Steel Hardware Elements used with Injection Adhesive System



INSTALLATION INSTRUCTIONS (HOLLOW BASE MATERIALS)

Drilling



1- Drill a hole into the base material with a rotary drill tool to the size and embedment for the required screen size (see *installation specifications for threaded rod in hollow concrete base material*). The tolerances of the drill bit used should meet the requirements of ANSI B212.15.

Precaution: Wear suitable eye and skin protection. Avoid inhalation of dusts during drilling and/or removal.

Hole Cleaning - Blow 2x, Brush 2x, Blow 2x



2 - Starting from the bottom or back of the anchor hole, blow the hole clean with a hand pump (min. volume 25 fl. oz. supplied by Powers Fasteners) or compressed air nozzle a minimum of *two* times (2x).

- Determine the wire brush diameter (see *hole cleaning equipment selection table*) and attach the brush with adaptor to a rotary drill tool or battery screw gun. Brush the hole with the selected wire brush a minimum of *two* times (2x). A brush extension (supplied by Powers Fasteners, Cat #08282) should be used for holes drilled deeper than the listed brush length.

The wire brush should be checked periodically during use. The brush must be replaced if it becomes worn (less than D_{min} , see *hole cleaning equipment selection table*) or does not come in contact with sides of the drill hole.

- Finally, blow the hole clean again a minimum of *two* times (2x)


When finished the hole should be clean and free of dust, debris, ice, grease, oil or other foreign material.

Preparing



3 - Check adhesive expiration date on cartridge label. Do not use expired product. Review Material Safety Data Sheet (MSDS) before use. Cartridge temperature must be between 32°F - 95°F (0°C - 35°C) when in use. Review gel (working) time and curing time table. Consideration should be given to the reduced gel (working) time of the adhesive in warm temperatures.

Attach a supplied mixing nozzle to the cartridge and load the cartridge into the correct dispensing tool. Always use a new mixing nozzle with new cartridges of adhesive; and for all work interruptions exceeding the published working time of the adhesive (see *gel time and curing time table*).



4 - Prior to inserting the anchor rod into the filled screen tube, the position of the embedment depth has to be marked on the anchor. Verify anchor element is straight and free of surface damage.



5 - Adhesive must be properly mixed to achieve published properties. Prior to dispensing adhesive into the drilled hole, separately dispense at least three full strokes of adhesive through the mixing nozzle until the adhesive is a consistent **gray** color. Do not attach a used nozzle when changing to a new cartridge. Review and note the published working and cure times (see *gel time and curing time table*) prior to injection of the mixed adhesive into the screen tube.

Installing



6 - Insert a screen tube of suitable length into the cleaned anchor hole.




7 - Fill the screen tube full with adhesive starting from the bottom or back of the tube. Slowly withdraw the mixing nozzle as the screen fills to avoid creating air pockets or voids. A plastic extension tube supplied by Powers Fasteners must be used with the mixing nozzle if the back of the screen tube cannot be reached.



8 - Prior to inserting the anchor rod into the screen tube inspect it to ensure that it is free of dirt, grease, oil or other foreign material.

Push the threaded rod into the screen tube while turning slightly to ensure positive distribution of the adhesive until the back of the tube is reached.

Curing and Fixing



9- Allow the adhesive anchor to cure to the specified full curing time prior to applying any load.

Do not disturb, torque or load the anchor until it is fully cured (see *gel time and curing time table*).




10- After full curing of the adhesive anchor, a fixture can be installed to the anchor and tightened up to the maximum torque (see *installation specifications for threaded rod in hollow concrete base material*) by using a calibrated torque wrench.

Take care not to exceed the maximum torque for the selected anchor.

AC100+Gold®

INSTALLATION INSTRUCTIONS (SOLID BASE MATERIALS)

Drilling



1- Drill a hole into the base material with a rotary hammer drill tool to the size and embedment required by the selected steel anchor element (see *installation specifications for threaded rod and reinforcing bar in solid concrete base material*). The tolerances of the carbide drill bit should meet the requirements of ANSI Standard B212.15.

Precaution: Wear suitable eye and skin protection. Avoid inhalation of dusts during drilling and/or removal.

Note! After drilling and prior to hole cleaning, all standing water in the drilled bore hole must be removed if present (e.g. vacuum, compressed air, etc.)



Hole Cleaning - Blow 4x, Brush 4x, Blow 4x



2a - Starting from the bottom or back of the anchor hole, blow the hole clean using a compressed air nozzle (min. 90 psi) or a hand pump (min. volume 25 fl. oz., supplied by Powers Fasteners) a minimum of *four* times (4x).


- Use a compressed air nozzle (min. 90 psi) or a hand pump (min. volume 25 fl. oz.) for anchor rod 3/8" to 3/4" diameter or reinforcing bar (rebar) sizes #3 to #6.

- Use a compressed air nozzle (min. 90 psi) for anchor rod 7/8" to 1-1/4" diameter and rebar sizes #7 to #10. A hand pump shall not be used with these anchor sizes.



2b - Determine wire brush diameter (see *hole cleaning equipment selection table*) and attach the brush with adaptor to a rotary drill tool or battery screwgun. Brush the hole with the selected wire brush a minimum of *four* times (4x). A brush extension (supplied by Powers Fasteners, Cat. #08282) should be used for holes drilled deeper than the listed brush length.


The wire brush diameter should be checked periodically during use. The brush must be replaced if it becomes worn (less than D_{min} , see *hole cleaning equipment selection table*) or does not come into contact with the sides of the drilled hole.



2c - Finally, blow the hole clean again a minimum of *four* times (4x).

- Use a compressed air nozzle (min. 90 psi) or a hand pump (min. volume 25 fl. oz.) for anchor rod 3/8" to 3/4" diameter or reinforcing bar (rebar) sizes #3 to #6.

- Use a compressed air nozzle (min. 90 psi) for anchor rod 7/8" to 1-1/4" diameter and rebar sizes #7 to #10. A hand pump shall not be used with these anchor sizes.




Preparing




3- Check adhesive expiration date on cartridge label. Do not use expired product. Review Material Safety Data Sheet (MSDS) before use. Cartridge temperature must be between 32°F - 95°F (0°C - 35°C) when in use. Review gel (working) and cure time table. Consideration should be given to the reduced gel time of the adhesive in warm temperatures.

Attach a supplied mixing nozzle to the cartridge and load the cartridge into the correct dispensing tool. Always use a new mixing nozzle with new cartridges of adhesive; and for all work interruptions exceeding the published working time of the adhesive (see *gel time and curing time table*).



4- Prior to inserting the anchor rod or rebar into the filled bore hole, the position of the embedment depth has to be marked on the anchor. Verify anchor element is straight and free of surface damage.




5- Adhesive must be properly mixed to achieve published properties. Prior to dispensing adhesive into the drilled hole, separately dispense at least three full strokes of adhesive through the mixing nozzle until the adhesive is a consistent **gray** color. Do not attach a used nozzle when changing to a new cartridge.


Review and note the published working and cure times (see *gel time and curing time table*) prior to injection of the mixed adhesive into the cleaned anchor hole.

INSTALLATION INSTRUCTIONS (SOLID BASE MATERIALS)

Installing



6- Fill the cleaned hole approximately two-thirds full with mixed adhesive starting from the bottom or back of the anchor hole. Slowly withdraw the mixing nozzle as the hole fills to avoid creating air pockets or voids. For embedment depth greater than 7-1/2" an extension nozzle (3/8" dia.) must be used with the mixing nozzle.




Piston plugs (see *adhesive piston plug table*) must be used with and attached to mixing nozzle and extension tube for horizontal and overhead installations with anchor rod from 3/4" to 1-1/4" diameter and rebar sizes #6 to #10. Insert piston plug to the back of the drilled hole and inject as described in the method above. During installation the piston plug will be naturally extruded from the drilled hole by the adhesive pressure.

Attention! Do not install anchors overhead without proper training and installation hardware provided by Powers Fasteners. Contact Powers for details prior to use.




7- The anchor should be free of dirt, grease, oil or other foreign material. Push clean threaded rod or reinforcing bar into the anchor hole while turning slightly to ensure positive distribution of the adhesive until the embedment depth is reached. Air pockets are present when the threaded rod or rebar springs or air pockets burst during installation. In case of air pockets: remove rod or rebar, let the adhesive harden, re-drill the hole and repeat the complete installation.




8- Be sure that the anchor is fully seated at the bottom of the hole and that some adhesive has flowed from the hole and all around the top of the anchor. If there is not enough adhesive in the hole, the installation must be repeated. The anchor shall not be moved after placement and during cure.

Curing and Loading



9- Allow the adhesive anchor to cure to the specified full curing time prior to applying any load (see *gel time and curing time table*).

Do not disturb, torque or load the anchor until it is fully cured.



10- After full curing of the adhesive anchor, a fixture can be installed to the anchor and tightened up to the maximum torque (see *installation specifications for threaded rod and reinforcing bar in solid concrete base material*) by using a calibrated torque wrench.

Take care not to exceed the maximum torque for the selected anchor.



AC100+Gold®

REFERENCE TABLES FOR INSTALLATION

Gel (working) Time and Curing Table

Temperature of base material		Gel (working) time	Full curing time
°F	°C		
14	-10	90 minutes	24 hours
23	-5	90 minutes	14 hours
32	0	45 minutes	7 hours
41	5	25 minutes	2 hours
50	10	15 minutes	90 minutes
68	20	6 minutes	45 minutes
86	30	4 minutes	25 minutes
95	35	2 minutes	20 minutes
104	40	1.5 minutes	15 minutes


The gel (working) times listed for 32°F to 95°F are also applicable for the temperature of the adhesive and use of mixing nozzles during installation. For installations in base material temperatures between 14°F and 23°F the cartridge temperature must be conditioned to between 68°F and 95°F (20°C - 35°C).

Hole Cleaning Equipment Selection Table for AC100+ Gold

Threaded rod diameter (inch)	Rebar size (no.)	ANSI drill bit diameter (inch)	Min. brush diameter, D _{min} (inches)	Brush length, L (inches)	Steel wire brush (Cat. #)	Blowout tool	Number of cleaning actions
Solid Base Material							
3/8	#3	7/16	0.475	6-3/4	08284	Hand-pump (Cat. #08280) or compressed air nozzle	4x blowing 4x brushing
1/2	#4	9/16	0.600	6-3/4	08285		
5/8	#5	11/16	0.735	7-7/8	08286		
5/8	#5	3/4	0.780	7-7/8	08278		
3/4	#6	7/8	0.920	7-7/8	08287	Compressed air nozzle only	4x blowing
7/8	#7	1	1.045	11-7/8	08288		
1	#8	1-1/8	1.175	11-7/8	08289		
1-1/4	#9	1-3/8	1.425	11-7/8	08290		
-	#10	1-1/2	1.550	11-7/8	08291		
Hollow Base Material							
3/8	-	1/2	0.600	6-3/4	08285	Hand pump (Cat. #08280) or compressed air nozzle	2x blowing 2x brushing 2x blowing
3/8	--	5/8	0.735	7-7/8	08286		
1/2	-	5/8	0.735	7-7/8	08286		
1/2	--	3/4	0.780	7-7/8	08278		
5/8	-	3/4	0.780	7-7/8	08278		
5/8	-	7/8	0.920	7-7/8	08287		

An SDS-plus adaptor (Cat. #08283) or Jacobs chuck style adaptor (Cat. #08296) is required to attach a steel wire brush to the drill tool. A brush extension (Cat. #08282) should be used for holes drilled deeper than the listed brush length.

Adhesive Piston Plugs

Threaded rod diameter (inch)	Rebar size (no.)	ANSI drill bit diameter (inch)	Plug Size (inch)	Plastic Plug (Cat. #)	Horizontal installations
3/4	#6	7/8	7/8	08300	
7/8	#7	1	1	08301	
1	#8	1-1/8	1-1/8	08303	
1-1/4	#9	1-3/8	1-3/8	08305	
-	#10	1-1/2	1-1/2	08309	

A plastic extension tube (3/8" dia.) must be used with piston plugs.



ORDERING INFORMATION

AC100+ Gold Cartridges

Cat No.	Fastenal SKU	Description	Std. Box	Std. Carton	Pallet
8462SD	2141216	AC100+ Gold 5 fl. oz. Push-Pak (DIY series)	12	36	-
8478SD	2141217	AC100+ Gold 10 fl. oz. Quik-Shot (DIY series)	12	-	972
8480SD	2141218	AC100+ Gold 8 fl. oz. dual cartridge	12	-	576
8486SD	2141219	AC100+ Gold 12 fl. oz. dual cartridge	12	-	864
8490SD	2141220	AC100+ Gold 28 fl. oz. dual cartridge	8	-	400

One AC100+ Gold mixing nozzle is packaged with each cartridge.

AC100+ Gold mixing nozzles must be used to ensure complete and proper mixing of the adhesive.

Cartridge System Mixing Nozzles

Cat No.	Fastenal SKU	Description	Std. Pack/Box	Std. Carton
08293	2141737	Extra mixing nozzle for AC100+ Gold (5 oz., 8 oz., 10 oz. & 12 oz.)	2	24
08294	2141738	Extra mixing nozzle (with a 8" extension) for AC100+ Gold 28 oz.	2	24
08281	2141725	Mixing nozzle extension, 8" minimum	2	24

Dispensing Tools for Injection Adhesive

Cat No.	Fastenal SKU	Description	Std. Box	Std. Carton
08437	2141235	Manual caulking gun for Push-Pak and Quik-Shot	1	12
08479	2141241	High performance caulking gun for Push-Pak and Quik-Shot	1	6
08484	2141242	AC100+ Gold 8 oz. standard all metal manual tool	1	6
08485	2141243	AC100+ Gold 8 oz., 10 oz. & 12 oz. high performance manual tool	1	20
08494	2141244	AC100+ Gold 28 oz. standard all metal manual tool	1	-
08495	-	AC100+ Gold 28 oz. high performance manual tool	1	-
08496	2141246	AC100+ Gold 28 oz. pneumatic tool	1	-
08444	2141239	AC100+ Gold 28 oz. cordless power tool	1	-

Hole Cleaning Tools and Accessories

Cat No.	Fastenal SKU	Description	Std. Box
08284	2141728	Wire brush for 7/16" ANSI hole (3/8" rod or #3 rebar), 6-3/4" length	1
08285	2141729	Wire brush for 9/16" ANSI hole (1/2" rod or #4 rebar), 6-3/4" length	1
08286	2141730	Wire brush for 11/16" ANSI hole (5/8" rod or #5 rebar), 7-7/8" length	1
08278	2141723	Wire brush for 3/4" ANSI hole (5/8" rod or #5 rebar), 7-7/8" length	1
08287	2141731	Wire brush for 7/8" ANSI hole (3/4" rod or #6 rebar), 7-7/8" length	1
08288	2141732	Wire brush for 1" ANSI hole (7/8" rod or #7 rebar), 11-7/8" length	1
08289	2141733	Wire brush for 1-1/8" ANSI hole (1" rod or #8 rebar), 11-7/8" length	1
08290	2141734	Wire brush for 1-3/8" ANSI hole (1-1/4" rod or #9 rebar), 11-7/8" length	1
08291	2141735	Wire brush for 1-1/2" ANSI hole (#10 rebar), 11-7/8" length	1
08283	2141727	SDS-plus adapter for steel brushes	1
08296	2141739	Standard drill adapter for steel brushes (e.g. Jacobs Chuck)	1
08282	2141726	Steel brush extension, 12" length	1
08280	2141724	Hand pump/dust blower (25 fl. oz. cylinder volume)	1
08292	2141736	Air compressor nozzle with extension, 18" length	1
08465	-	Adjustable torque wrench with 1/2" square drive (10 to 150 ft.-lbs.)	1
08466	-	Adjustable torque wrench with 1/2" square drive (25 to 250 ft.-lbs.)	1
52073	-	Adhesive cleaning kit, includes 4 wire brushes (08284, 08285, 08286, 08287), s steel brush extension (08282), SDS-plus adapter (08283), standard drill adapter (08296), hand pump/dust blower (08280), gloves and safety glasses	1

Stainless Steel Screen Tubes

Cat. No.	Fastenal SKU	Description	Drill Diameter	Standard Carton
07961	2141258	3/8" x 3-1/2" Screen Tube	1/2"	25
07962	2141259	3/8" x 6" Screen Tube*	1/2"	25
07963	2141260	3/8" x 8" Screen Tube*	1/2"	25
07964	2141261	3/8" x 10" Screen Tube*	1/2"	25
07959	2141256	3/8" x 12" Screen Tube*	1/2"	25
07965	2141262	1/2" x 3-1/2" Screen Tube	5/8"	25
07966	2141263	1/2" x 6" Screen Tube*	5/8"	25
07967	2141264	1/2" x 8" Screen Tube*	5/8"	25
07968	2141265	1/2" x 10" Screen Tube*	5/8"	25
07969	2141266	5/8" x 4-1/2" Screen Tube	3/4"	20
07970	2141267	5/8" x 6" Screen Tube	3/4"	20
07971	2141268	5/8" x 8" Screen Tube*	3/4"	20
07972	2141269	5/8" x 10" Screen Tube*	3/4"	20

Screen tubes are made from a 300 series stainless steel. The nominal diameter of the screen listed indicates the matching rod diameter.

*Includes extension tubing.



AC100+Gold®

SD PERFORMANCE DATA

Concrete Tension Design Information for Threaded Rod and Reinforcing Bar in Normal-Weight Concrete (For use with load combinations taken from ACI 318 Section 9.2)^{1,2,3,4}

Design Information	Symbol	Units	Nominal Rod Diameter (inch) ¹								
			3/8	1/2	5/8	3/4	7/8	1	-	1-1/4	
			#3	#4	#5	#6	#7	#8	#9	#10	
Minimum Embedment	$h_{e,min}$	in. (mm)	2-3/8 (60)	2-3/4 (70)	3-1/8 (79)	3-1/2 (89)	3-1/2 (89)	4 (102)	4-1/2 (114)	5 (127)	
CONCRETE BREAKOUT STRENGTH IN TENSION											
Effectiveness factor for cracked concrete	k_{cr}	-	Not applicable	17	17	17	17	17	17	17	
Effectiveness factor for uncracked concrete	k_{uncr}	-	24	24	24	24	24	24	24	24	
Modification factor for uncracked concrete	Ψ_{cN}	-	For all design cases use $\Psi_{cN} = 1.0$								
Critical edge distance	c_{ac}	in.	$C_{ac} = h_{ef} \cdot \left(\frac{\min(\tau_{k,uncr}; \tau_{k,max})}{1160} \right)^{0.4} \cdot \max\left[\left(3.1 - 0.7 \frac{h}{h_{ef}} \right); 1.4 \right]$								
		(mm)	$C_{ac} = h_{ef} \cdot \left(\frac{\min(\tau_{k,uncr}; \tau_{k,max})}{8} \right)^{0.4} \cdot \max\left[\left(3.1 - 0.7 \frac{h}{h_{ef}} \right); 1.4 \right]$								
Reduction factor for concrete breakout strength	ϕ	-	Condition B = 0.65								
BOND STRENGTH IN TENSION FOR TEMPERATURE RANGE A⁴ Maximum long term service temperature = 75° (24°C), Maximum short term service temperature = 104° (40°C)											
Dry hole	Reduction factor for bond strength	ϕ_d	-	0.65							
	Characteristic bond strength, cracked concrete (2,500 psi)	$\tau_{k,cr}$	psi (N/mm ²)	Not applicable	871 (6.0)	907 (6.3)	907 (6.3)	907 (6.3)	918 (6.3)	918 (6.3)	918 (6.3)
	Characteristic bond strength, uncracked concrete (2,500 psi)	$\tau_{k,uncr}$	psi (N/mm ²)	1,450 (10.0)	1,450 (10.0)	1,450 (10.0)	1,450 (10.0)	1,450 (10.0)	1,305 (9.0)	1,160 (8.0)	1,030 (7.1)
Water saturated hole	Reduction factor for bond strength	ϕ_{ws}	-	0.55							
	Additional factor for water saturated concrete	κ_{ws}	-	1.0	1.0	1.0	1.0	1.0	1.0	1.0	
Water-filled hole	Reduction factor for bond strength	ϕ_{wf}	-	0.45							
	Additional factor for water-filled hole condition	κ_{wf}	-	0.78	0.78	0.78	0.78	0.70	0.69	0.68	0.67
BOND STRENGTH IN TENSION FOR TEMPERATURE RANGE B⁴ Maximum long term service temperature = 122°F (50°C), Maximum short term service temperature = 176° (80°C)											
Dry hole	Reduction factor for bond strength	ϕ_d	-	0.65							
	Characteristic bond strength, cracked concrete (2,500 psi)	$\tau_{k,cr}$	psi (N/mm ²)	Not applicable	541 (3.7)	563 (3.9)	563 (3.9)	563 (3.9)	563 (3.9)	563 (3.9)	563 (3.9)
	Characteristic bond strength, uncracked concrete (2,500 psi)	$\tau_{k,uncr}$	psi (N/mm ²)	870 (6.0)	870 (6.0)	870 (6.0)	870 (6.0)	870 (6.0)	798 (5.5)	696 (4.8)	638 (4.4)
Water saturated hole	Reduction factor for bond strength	ϕ_{ws}	-	0.55							
	Additional factor for water saturated concrete	κ_{ws}	-	1.0	1.0	1.0	1.0	1.0	1.0	1.0	
Water-filled hole	Reduction factor for bond strength	ϕ_{wf}	-	0.45							
	Additional factor for water-filled hole condition	κ_{wf}	-	0.78	0.78	0.78	0.78	0.70	0.69	0.68	0.67

- The data in this table is intended to be used together with the design provisions of ACI 318 Appendix D and ICC-ES AC308 Annex A, Section 3.3 and ESR-2582.
- Installation must comply with published instructions and details. Periodic special inspection must be performed where required by code or the Authority Having Jurisdiction (AHJ). See ICC-ES AC308 Annex A, Section 14.4 and ESR-2582.
- Long term concrete temperatures are roughly constant over significant periods of time. Short-term elevated temperatures are those that occur over brief intervals, e.g. as a result of diurnal cycling.
- For load combinations consisting of short term loads only such as wind, bond strength may be increased by 40% for Temperature Range B.



SD PERFORMANCE DATA

Concrete Shear Design Information for Threaded Rod and Reinforcing Bar in Normal-Weight Concrete (For use with load combinations taken from ACI 318 Section 9.2)^{1,2,3}

Design Information	SYMBOL	UNITS	Nominal Rod Diameter (inch) ¹							
			3/8	1/2	5/8	3/4	7/8	1	-	1-1/4
			#3	#4	#5	#6	#7	#8	#9	#10
Minimum Embedment	$h_{ef,min}$	in. (mm)	2-3/8 (60)	2-3/4 (70)	3-1/8 (79)	3-1/2 (89)	3-1/2 (89)	4 (102)	4-1/2 (114)	5 (127)
CONCRETE BREAKOUT STRENGTH IN SHEAR										
Load bearing length of anchor	ℓ_e	in. (mm)	h_{ef} or $8d$, whichever is less							
Reduction factor for concrete breakout strength	ϕ	-	Condition B = 0.70							
PRYOUT STRENGTH IN SHEAR										
Coefficient for pryout strength	κ_{cp}	-	1.0 for hef < 2.5 in., 2.0 for hef ≥ 2.5 in.							
Reduction factor for pryout strength	ϕ	-	Condition B = 0.70							

1. The data in this table is intended to be used together with the design provisions of ACI 318 Appendix D and ICC-ES AC308 Annex A, Section 3.3 and ESR-2582.
2. Installation must comply with published instructions and details. Periodic special inspection must be performed where required by code or the Authority Having Jurisdiction (AHJ). See ICC-ES AC308 Annex A, Section 14.4 and ESR-2582.
3. For load combinations consisting of short term loads only such as wind, bond strength may be increased by 40% for Temperature Range B.

Bond Strength Determination				
Concrete State	Hole Drilling Method	Installation Conditions	Bond Strength	Strength Reduction Factor
Uncracked concrete	Hammer Drill	Dry Concrete	$\tau_{k,uncr}$	ϕ_d
		Water-saturated concrete	$\tau_{k,uncr} \cdot \kappa_{ws}$	ϕ_{ws}
		Water-filled holes	$\tau_{k,uncr} \cdot \kappa_{wf}$	ϕ_{wf}
Cracked Concrete	Hammer Drill	Dry Concrete	$\tau_{k,cr}$	ϕ_d
		Water-saturated concrete	$\tau_{k,cr} \cdot \kappa_{ws}$	ϕ_{ws}
		Water-filled holes	$\tau_{k,cr} \cdot \kappa_{wf}$	ϕ_{wf}



SD PERFORMANCE DATA

- Tabular values are provided for illustration and are applicable for single anchors installed in uncracked normal-weight concrete with minimum slab thickness, $h_a = h_{min}$ and with the following conditions:
 - c_{cr} is greater than or equal to the critical edge distance, c_{ac} where $c_{ac} = 2.7 h_{ef}$
 - c_2 is greater than or equal to 1.5 times c_{cr}
- Calculations were performed according to ACI 318-05 Appendix D and ICC-ES AC308 Annex A, Section 3.3. The load level corresponding to the failure mode is listed (e.g. For tension: steel, concrete breakout or bond strength; For shear: steel, concrete breakout or pryout strength). The lowest load level controls.
- Strength reduction factors (ϕ) for steel strength and concrete breakout strength are based on ACI 318 Section 9.2 for load combinations. Condition B was assumed.
- Strength reduction factors (ϕ) for bond strength are determined from reliability testing and qualification in accordance with ICC-ES AC308 and are tabulated in this product information and in ESR-2582.
- Tabular values are permitted for static loads only, seismic loading is not considered with these tables. Periodic special inspection must be performed where required by code or the Authority Having Jurisdiction (AHJ). See ICC-ES AC308 Annex A, Section 14.4 and ESR-2582.
- Tabular values are not permitted for anchors subjected to tension resulting from sustained loading. Please see ICC-ES AC308 Annex A, Section 3.3 and ESR-2582 for the supplement design requirement for this loading condition.
- For designs that include combined tension and shear, the interaction of tension and shear loads must be calculated in accordance with ACI 318-05 Appendix D.
- Interpolation is not permitted to be used with the tabular values. For intermediate base material compressive strengths, please see ACI 318-05 Appendix D, ICC-ES AC308 Annex A, Section 3.3 and information included in this product supplement. For other design conditions including seismic considerations please see ACI 318-05 Appendix D and ICC-ES AC308 Annex A, Section 3.3 and ESR-2582.
- Long term concrete temperatures are roughly constant over significant periods of time. Short-term elevated temperatures are those that occur over brief intervals, e.g. as a result of diurnal cycling.



Tension and Shear Design Strength Installed in Uncracked Concrete, Drilled with a Hammer-Drill and Carbide Bit in a Dry Hole Condition, for Temperature Range A (Bond or Concrete Strength)

Maximum long term service temperature = 75°F (24°C), Maximum short term service temperature = 104°F (40°C)

Nominal Rod/Rebar Size (in. or #)	Embed. Depth h_{ef} (in.)	Minimum Concrete Compressive Strength, f'_c (psi)									
		2,500		3,000		4,000		6,000		8,000	
		ϕN_{cb} or ϕN_{ta} Tension (lbs.)	ϕV_{cb} or ϕV_{cp} Shear (lbs.)	ϕN_{cb} or ϕN_{ta} Tension (lbs.)	ϕV_{cb} or ϕV_{cp} Shear (lbs.)	ϕN_{cb} or ϕN_{ta} Tension (lbs.)	ϕV_{cb} or ϕV_{cp} Shear (lbs.)	ϕN_{cb} or ϕN_{ta} Tension (lbs.)	ϕV_{cb} or ϕV_{cp} Shear (lbs.)	ϕN_{cb} or ϕN_{ta} Tension (lbs.)	ϕV_{cb} or ϕV_{cp} Shear (lbs.)
3/8 or #3	2-3/8	2,635	1,860	2,695	2,035	2,790	2,350	2,930	2,880	3,030	3,265
	3	3,330	2,565	3,405	2,810	3,525	3,245	3,700	3,975	3,830	4,590
	4-1/2	4,995	4,255	5,105	4,660	5,285	5,380	5,550	6,590	5,745	7,610
1/2 or #4	2-3/4	3,555	2,480	3,895	2,715	4,310	3,135	4,520	3,840	4,680	4,435
	4	5,920	4,230	6,055	4,630	6,265	5,350	6,580	6,550	6,810	7,565
	6	8,885	7,150	9,080	7,835	9,400	9,045	9,865	11,080	10,215	12,795
5/8 or #5	3-1/8	4,310	3,260	4,720	3,570	5,450	4,125	6,425	5,050	6,650	5,830
	5	8,720	6,420	9,460	7,030	9,790	8,120	10,280	9,945	10,640	11,480
	7-1/2	13,880	10,945	14,185	11,990	14,685	13,840	15,415	16,955	15,960	19,575
3/4 or #6	3-1/2	5,105	4,350	5,595	4,765	6,460	5,500	7,910	6,740	8,935	7,780
	6	11,465	9,365	12,560	10,255	14,095	11,845	14,800	14,505	15,320	16,750
	9	19,985	15,905	20,430	17,425	21,145	20,120	22,200	24,640	22,980	28,455
7/8 or #7	3-1/2	5,105	4,770	5,595	5,225	6,460	6,035	7,910	7,395	9,135	8,535
	7	14,445	12,685	15,825	13,895	18,275	16,045	20,145	19,650	20,850	22,690
	10-1/2	26,540	21,580	27,805	23,640	28,780	27,295	30,215	33,430	31,280	38,600
1 or #8	4	6,240	6,195	6,835	6,790	7,895	7,840	9,665	9,600	11,160	11,085
	8	17,650	16,510	19,335	18,085	22,325	20,885	23,680	25,580	24,510	29,535
	12	31,980	28,115	32,685	30,795	33,835	35,560	35,520	43,555	36,770	50,290
#9	4-1/2	7,445	8,090	8,155	8,860	9,420	10,230	11,535	12,530	13,320	14,465
	9	21,060	21,295	23,070	23,325	25,375	26,935	26,640	32,985	27,575	38,090
	13-1/2	35,975	36,065	36,770	39,510	38,065	45,620	39,960	55,875	41,365	64,515
1 1/4	5	8,720	9,605	9,555	10,525	11,030	12,150	13,510	14,880	15,115	17,185
	10	24,665	25,670	26,875	28,125	27,815	32,475	29,205	39,770	30,230	45,925
	15	39,435	43,775	40,310	47,950	41,725	55,370	43,805	67,810	45,345	78,305
#10	5	8,720	9,915	9,555	10,860	11,030	12,545	13,510	15,360	15,115	17,740
	10	24,665	26,175	26,875	28,675	27,815	33,110	29,205	40,550	30,230	46,825
	15	39,435	44,390	40,310	48,625	41,725	56,150	43,805	68,765	45,345	79,405

Legend Concrete Breakout Strength Bond Strength/Pryout Strength



SD PERFORMANCE DATA

Tension and Shear Design Strength Installed in Uncracked Concrete, Drilled with a Hammer-Drill and Carbide Bit in a Dry Hole Condition, for Temperature Range B (Bond or Concrete Strength)
 -see notes on previous page

Maximum long term service temperature = 122°F (50°C), Maximum short term service temperature = 176°F (80°C)



		Minimum Concrete Compressive Strength, f'c (psi)									
Nominal Rod/Rebar Size (in. or #)	Embed. Depth h _{ef} (in.)	2,500		3,000		4,000		6,000		8,000	
		ϕN_{cb} or ϕN_a Tension (lbs.)	ϕV_{cb} or ϕV_{cp} Shear (lbs.)	ϕN_{cb} or ϕN_a Tension (lbs.)	ϕV_{cb} or ϕV_{cp} Shear (lbs.)	ϕN_{cb} or ϕN_a Tension (lbs.)	ϕV_{cb} or ϕV_{cp} Shear (lbs.)	ϕN_{cb} or ϕN_a Tension (lbs.)	ϕV_{cb} or ϕV_{cp} Shear (lbs.)	ϕN_{cb} or ϕN_a Tension (lbs.)	ϕV_{cb} or ϕV_{cp} Shear (lbs.)
3/8 or #3	2-3/8	1,580	1,705	1,615	1,740	1,675	1,805	1,760	1,895	1,820	1,960
	3	2,000	2,565	2,045	2,810	2,115	3,245	2,220	3,975	2,300	4,590
	4-1/2	3,000	4,255	3,065	4,660	3,170	5,380	3,330	6,590	3,445	7,425
1/2 or #4	2-3/4	2,445	2,480	2,495	2,715	2,585	3,135	2,715	3,840	2,810	4,435
	4	3,555	4,230	3,630	4,630	3,760	5,350	3,945	6,550	4,085	7,565
	6	5,330	7,150	5,450	7,835	5,640	9,045	5,920	11,080	6,130	12,795
5/8 or #5	3-1/8	3,470	3,260	3,545	3,570	3,670	4,125	3,855	5,050	3,990	5,830
	5	5,550	6,420	5,675	7,030	5,875	8,120	6,165	9,945	6,385	11,480
	7-1/2	8,330	10,945	8,510	11,990	8,810	13,840	9,250	16,955	9,575	19,575
3/4 or #6	3-1/2	4,665	4,350	4,765	4,765	4,935	5,500	5,180	6,740	5,360	7,780
	6	7,995	9,365	8,170	10,255	8,460	11,845	8,880	14,505	9,190	16,750
	9	11,990	15,905	12,255	17,425	12,690	20,120	13,320	24,640	13,790	28,455
7/8 or #7	3-1/2	5,105	4,770	5,560	5,225	5,755	6,035	6,045	7,395	6,255	8,535
	7	10,880	12,685	11,120	13,895	11,515	16,045	12,085	19,650	12,510	22,690
	10-1/2	16,320	21,580	16,685	23,640	17,270	27,295	18,130	33,430	18,765	38,600
1 or #8	4	6,240	6,195	6,660	6,790	6,895	7,840	7,240	9,600	7,495	11,085
	8	13,035	16,510	13,325	18,085	13,795	20,885	14,480	25,580	14,990	29,535
	12	19,555	28,115	19,985	30,795	20,690	35,560	21,720	43,555	22,485	48,425
#9	4-1/2	7,195	8,090	7,355	8,860	7,615	10,230	7,990	12,530	8,275	14,465
	9	14,390	21,295	14,710	23,325	15,225	26,935	15,985	32,985	16,545	35,635
	13-1/2	21,585	36,065	22,065	39,510	22,840	45,620	23,975	51,640	24,820	53,455
1-1/4	5	8,145	9,605	8,325	10,525	8,615	12,150	9,045	14,880	9,360	17,185
	10	16,285	25,670	16,645	28,125	17,230	32,475	18,090	38,960	18,725	40,330
	15	24,430	43,775	24,970	47,950	25,845	55,370	27,135	58,440	28,085	60,495
#10	5	8,145	9,915	8,325	10,860	8,615	12,545	9,045	15,360	9,360	17,740
	10	16,285	26,175	16,645	28,675	17,230	33,110	18,090	38,960	18,725	40,330
	15	24,430	44,390	24,970	48,625	25,845	55,665	27,135	58,440	28,085	60,495

Legend Concrete Breakout Strength Bond Strength/Pryout Strength

Factored bond or concrete strength must be checked against factored steel strength to determine the controlling ultimate load.
 Factored tension design strength = $\min\{\phi N_{cb} \text{ or } \phi N_a \text{ or } \phi N_{sa}\}$ and factored shear design strength = $\min\{\phi V_{cb} \text{ or } \phi V_{cs} \text{ or } \phi V_{cp}\}$



AC100+Gold®

SD PERFORMANCE DATA

Tension and Shear Design Strength Installed in Cracked Concrete, Drilled with a Hammer-Drill and Carbide Bit in a Dry Hole Condition, for Temperature Range A (Bond or Concrete Strength)

Maximum long term service temperature = 75°F (24°C), Maximum short term service temperature = 104°F (40°C)



Minimum Concrete Compressive Strength, f'c (psi)

Nominal Rod/Rebar Size (in. or #)	Embed. Depth h _{ef} (in.)	2,500		3,000		4,000		6,000		8,000	
		ϕN_{cb} or ϕN_s Tension (lbs.)	ϕV_{cb} or ϕV_{sp} Shear (lbs.)	ϕN_{cb} or ϕN_s Tension (lbs.)	ϕV_{cb} or ϕV_{sp} Shear (lbs.)	ϕN_{cb} or ϕN_s Tension (lbs.)	ϕV_{cb} or ϕV_{sp} Shear (lbs.)	ϕN_{cb} or ϕN_s Tension (lbs.)	ϕV_{cb} or ϕV_{sp} Shear (lbs.)	ϕN_{cb} or ϕN_s Tension (lbs.)	ϕV_{cb} or ϕV_{sp} Shear (lbs.)
1/2 or #4	2-3/4	2,445	1,770	2,500	1,940	2,585	2,240	2,715	2,740	2,810	3,165
	4	3,555	3,020	3,635	3,310	3,765	3,820	3,950	4,680	4,090	5,405
	6	5,335	5,110	5,455	5,595	5,645	6,460	5,925	7,915	6,135	9,140
5/8 or #5	3-1/8	3,050	2,330	3,345	2,550	3,825	2,945	4,020	3,610	4,160	4,165
	5	5,790	4,585	5,915	5,020	6,125	5,800	6,430	7,100	6,655	8,200
	7-1/2	8,680	7,815	8,875	8,565	9,185	9,885	9,645	12,110	9,980	13,985
3/4 or #6	3-1/2	3,620	3,105	3,965	3,405	4,575	3,930	5,400	4,815	5,590	5,555
	6	8,120	6,690	8,520	7,325	8,820	8,460	9,260	10,360	9,585	11,965
	9	12,500	11,360	12,780	12,445	13,225	14,370	13,885	17,600	14,375	20,325
7/8 or #7	3-1/2	3,620	3,410	3,965	3,735	4,575	4,310	5,605	5,280	6,470	6,095
	7	10,230	9,060	11,210	9,925	12,000	11,460	12,600	14,035	13,045	16,210
	10-1/2	17,015	15,415	17,395	16,885	18,005	19,495	18,900	23,880	19,565	27,570
1 or #8	4	4,420	4,425	4,840	4,850	5,590	5,600	6,845	6,860	7,905	7,920
	8	12,500	11,795	13,695	12,920	15,675	14,920	16,460	18,270	17,035	21,095
	12	22,225	20,080	22,715	21,995	23,515	25,400	24,685	31,110	25,555	35,920
#9	4-1/2	5,275	5,775	5,780	6,330	6,670	7,305	8,170	8,950	9,435	10,335
	9	14,920	15,210	16,340	16,660	18,870	19,240	21,085	23,560	21,825	27,205
	13-1/2	27,405	25,760	29,100	28,220	30,120	32,585	31,625	39,910	32,735	46,085
1-1/4	5	6,175	6,860	6,765	7,515	7,815	8,680	9,570	10,630	11,050	12,275
	10	17,470	18,335	19,140	20,090	22,100	23,195	26,030	28,410	26,940	32,805
	15	32,095	31,265	35,160	34,250	37,190	39,550	39,040	48,435	40,415	55,930
#10	5	6,175	7,085	6,765	7,760	7,815	8,960	9,570	10,970	11,050	12,670
	10	17,470	18,695	19,140	20,480	22,100	23,650	26,030	28,965	26,940	33,445
	15	32,095	31,705	35,160	34,735	37,190	40,105	39,040	49,120	40,415	56,720

Legend Concrete Breakout Strength Bond Strength/Pryout Strength



SD PERFORMANCE DATA



Tension and Shear Design Strength Installed in Cracked Concrete, Drilled with a Hammer-Drill and Carbide Bit in a Dry Hole Condition, for Temperature Range B (Bond or Concrete Strength)

Maximum long term service temperature = 122°F (50°C), Maximum short term service temperature = 176°F (80°C)

Minimum Concrete Compressive Strength, f'c (psi)											
Nominal Rod/Rebar Size (in. or #)	Embed. Depth h _{ef} (in.)	2,500		3,000		4,000		6,000		8,000	
		ϕN_{cb} or ϕN_t Tension (lbs.)	ϕV_{cb} or ϕV_s Shear (lbs.)	ϕN_{cb} or ϕN_t Tension (lbs.)	ϕV_{cb} or ϕV_s Shear (lbs.)	ϕN_{cb} or ϕN_t Tension (lbs.)	ϕV_{cb} or ϕV_s Shear (lbs.)	ϕN_{cb} or ϕN_t Tension (lbs.)	ϕV_{cb} or ϕV_s Shear (lbs.)	ϕN_{cb} or ϕN_t Tension (lbs.)	ϕV_{cb} or ϕV_s Shear (lbs.)
1/2 or #4	2-3/4	1,520	1,770	1,555	1,940	1,605	2,240	1,685	2,740	1,745	3,165
	4	2,210	3,020	2,260	3,310	2,340	3,820	2,455	4,680	2,540	5,405
	6	3,315	5,110	3,390	5,595	3,505	6,460	3,680	7,915	3,810	8,210
5/8 or #5	3-1/8	2,245	2,330	2,295	2,550	2,375	2,945	2,495	3,610	2,580	4,165
	5	3,595	4,585	3,670	5,020	3,800	5,800	3,990	7,100	4,130	8,200
	7-1/2	5,390	7,815	5,510	8,565	5,700	9,885	5,985	12,110	6,195	13,345
3/4 or #6	3-1/2	3,020	3,105	3,085	3,405	3,195	3,930	3,350	4,815	3,470	5,555
	6	5,175	6,690	5,290	7,325	5,475	8,460	5,745	10,360	5,950	11,965
	9	7,760	11,360	7,930	12,445	8,210	14,370	8,620	17,600	8,925	19,220
7/8 or #7	3-1/2	3,520	3,410	3,600	3,735	3,725	4,310	3,910	5,280	4,050	6,095
	7	7,040	9,060	7,195	9,925	7,450	11,460	7,820	14,035	8,095	16,210
	10-1/2	10,565	15,415	10,795	16,885	11,175	19,495	11,735	23,880	12,145	26,160
1 or #8	4	4,420	4,425	4,700	4,850	4,865	5,600	5,110	6,860	5,285	7,920
	8	9,195	11,795	9,400	12,920	9,730	14,920	10,215	18,270	10,575	21,095
	12	13,795	20,080	14,100	21,995	14,595	25,400	15,325	31,110	15,860	34,165
#9	4-1/2	5,275	5,775	5,780	6,330	6,160	7,305	6,465	8,950	6,690	10,335
	9	11,640	15,210	11,900	16,660	12,315	19,240	12,930	23,560	13,385	27,205
	13-1/2	17,460	25,760	17,845	28,220	18,475	32,585	19,395	39,910	20,075	43,240
1-1/4	5	6,175	6,860	6,765	7,515	7,600	8,680	7,980	10,630	8,260	12,275
	10	14,370	18,335	14,690	20,090	15,205	23,195	15,965	28,410	16,525	32,805
	15	21,555	31,265	22,035	34,250	22,805	39,550	23,945	48,435	24,785	53,385
#10	5	6,175	7,085	6,765	7,760	7,600	8,960	7,980	10,970	8,260	12,670
	10	14,370	18,695	14,690	20,480	15,205	23,650	15,965	28,965	16,525	33,445
	15	21,555	31,705	22,035	34,735	22,805	40,105	23,945	49,120	24,785	53,385

Legend Concrete Breakout Strength Bond Strength/Pryout Strength



SD PERFORMANCE DATA



Tension Design of Steel Elements (Steel Strength)

Nominal Rod/Rebar Size (in. or No.)	Steel Elements - Threaded Rod and Reinforcing Bar										
	A36 and F1554, Grade 36	F1554, Grade 55	A449	A193, Grade B7	F593 Condition CW	A 193 Grade B8/B8M, Class 1	A 193 Grade B8/B8M2, Class 2B	A615, Grade 75	A615, Grade 60	A706, Grade 60	A615, Grade 40
	ϕN_{sa} Tension (lbs.)	ϕN_{sa} Tension (lbs.)	ϕN_{sa} Tension (lbs.)	ϕN_{sa} Tension (lbs.)	ϕN_{sa} Tension (lbs.)	ϕN_{sa} Tension (lbs.)	ϕN_{sa} Tension (lbs.)	ϕN_{sa} Tension (lbs.)	ϕN_{sa} Tension (lbs.)	ϕN_{sa} Tension (lbs.)	ϕN_{sa} Tension (lbs.)
3/8 or #3	3,395	4,390	7,020	7,315	5,070	4,390	5,560	7,150	6,435	6,600	4,290
1/2 or #4	6,180	7,990	12,780	13,315	9,230	7,990	10,120	13,000	11,700	12,000	7,800
5/8 or #5	9,830	12,715	20,340	21,190	14,690	12,715	16,105	20,150	18,135	18,600	12,090
3/4 or #6	14,575	18,845	30,150	31,405	21,775	18,845	23,870	28,600	25,740	26,400	17,160
7/8 or #7	20,100	25,990	41,580	43,315	30,030	25,990	32,920	39,000	35,100	36,000	23,400
1 or #8	26,360	34,090	54,540	56,815	39,390	34,090	43,180	51,350	46,215	47,400	30,810
#9	-	-	-	-	-	-	-	65,000	58,500	60,000	39,000
1-1/4	42,150	54,505	87,210	90,845	62,985	54,505	69,040	-	-	-	-
#10	-	-	-	-	-	-	-	82,550	74,295	76,200	49,530

Legend Steel Strength



SD PERFORMANCE DATA



Shear Design of Steel Elements (Steel Strength)

Steel Elements - Threaded Rod and Reinforcing Bar

Nominal Rod/Rebar Size (in. or No.)	A36 and F1554, Grade 36	F1554, Grade 55	A449	A193, Grade B7	F593 Condition CW	A 193 Grade B8/B8M, Class 1	A 193 Grade B8/B8M2, Class 2B	A615, Grade 75	A615, Grade 60	A706, Grade 60	A615, Grade 40
	ϕV_{sa} Shear (lbs.)	ϕV_{sa} Shear (lbs.)	ϕV_{sa} Shear (lbs.)	ϕV_{sa} Shear (lbs.)	ϕV_{sa} Shear (lbs.)	ϕV_{sa} Shear (lbs.)	ϕV_{sa} Shear (lbs.)	ϕV_{sa} Shear (lbs.)	ϕV_{sa} Shear (lbs.)	ϕV_{sa} Shear (lbs.)	ϕV_{sa} Shear (lbs.)
3/8 or #3	1,765	2,280	3,650	3,805	2,810	2,280	2,890	3,960	3,565	3,430	2,375
1/2 or #4	3,210	4,155	6,645	6,925	5,110	4,155	5,260	7,200	6,480	6,240	4,320
5/8 or #5	5,110	6,610	10,580	11,020	8,135	6,610	8,375	11,160	10,045	9,670	6,695
3/4 or #6	7,580	9,800	15,680	16,330	12,060	9,800	12,410	15,840	14,255	13,730	9,505
7/8 or #7	10,450	13,515	21,620	22,525	16,630	13,515	17,120	21,600	19,440	18,720	12,960
1 or #8	13,710	17,725	28,360	29,545	21,815	17,725	22,450	28,440	25,595	24,650	17,065
#9	-	-	-	-	-	-	-	36,000	32,400	31,200	21,600
1-1/4	21,920	28,345	45,350	47,240	34,885	28,345	35,900	-	-	-	-
#10	-	-	-	-	-	-	-	45,720	41,150	39,625	27,430

Legend Steel Strength



AC100+Gold®

ASD PERFORMANCE DATA



Allowable Load Capacities for AC100+ Gold Installed into Normal-Weight Concrete with Threaded Rod and Reinforcing Bar (Based on Bond Strength/Concrete Capacity)^{1,2,3,4,5,6}

Nominal Rod Diameter or Rebar Size (in. or #)	Minimum Embedment Depth (in.)	Minimum Concrete Compressive Strength, (f'c)			
		3,000 psi	4,000 psi	5,000 psi	6,000 psi
		Tension (lbs)			
3/8 or #3	2-3/8	1,045	1,085	1,115	1,145
	3-1/2	1,540	1,600	1,645	1,685
	4-1/2	1,980	2,055	2,115	2,170
1/2 or #4	2-3/4	1,720	1,785	1,840	1,885
	4-3/8	2,740	2,845	2,925	2,995
	6	3,755	3,900	4,015	4,110
5/8 or #5	3-1/8	2,420	2,515	2,585	2,650
	5-1/4	4,140	4,300	4,425	4,530
	7-1/2	5,960	6,190	6,370	6,525
3/4 or #6	3-1/2	2,870	2,980	3,065	3,140
	6-1/4	5,795	6,015	6,190	6,340
	9	8,715	9,050	9,315	9,540
7/8 or #7	3-1/2	2,870	2,980	3,065	3,140
	7	7,905	8,205	8,450	8,650
	10-1/2	12,940	13,435	13,830	14,160
1 or #8	4	3,505	3,640	3,745	3,835
	8	10,030	10,410	10,720	10,975
	12	16,555	17,185	17,690	18,115
1-1/4 or #10	5	4,900	5,085	5,235	5,360
	10	14,200	14,740	15,175	15,540
	15	23,500	24,395	25,115	25,715

1. Allowable load capacities listed are calculated using an applied safety factor of 4.0 which includes assessment of freezing/thawing conditions and sensitivity to sustained loads (e.g. creep resistance). Consideration of safety factors of 10 or higher may be necessary depending on the application, such as life safety or overhead.
2. Linear interpolation may be used to determine allowable loads for intermediate embedments and compressive strengths.
3. The tabulated load values are applicable to single anchors installed at critical edge and spacing distances and where the minimum member thickness is 2.5 times the embedment depth.
4. The tabulated load values are applicable for dry concrete. Holes must be drilled with a hammer drill and an ANSI carbide drill bit. Installations in wet concrete or in water-filled holes may require a reduction in capacity. Contact Powers Fasteners for more information concerning these installation conditions.
5. Adhesives experience reductions in capacity at elevated temperatures. See the In-Service Temperature chart for allowable loads.
6. Allowable bond strength/concrete capacity must be checked against allowable steel strength to determine the controlling allowable load. Allowable shear capacity is controlled by allowable steel strength for the given conditions.

In-Service Temperature Chart for Allowable Load Capacities¹

Base Material Temperature		Reduction Factor For Temperature
°F	°C	
14	-10	1.00
23	-5	1.00
32	0	1.00
41	5	1.00
50	10	1.00
68	20	1.00
86	30	0.93
104	40	0.86
122	50	0.80
140	60	0.73
158	70	0.66
176	80	0.59

1. Linear interpolation may be used to derive reduction factors for base material temperatures between those listed.



ASD PERFORMANCE DATA



Allowable Load Capacities for AC100+ Gold Installed into Normal-Weight Concrete with Threaded Rod and Reinforcing Bar (Based on Steel Strength)^{1,2,3}

Nominal Rod Diameter or Rebar Size (in. or #)	Steel Elements - Threaded Rod and Reinforcing Bar							
	A36 or F1554		A 193, Grade B7		F 593, CW (SS)		Grade 60 Rebar	
	Tension (lbs)	Shear (lbs)	Tension (lbs)	Shear (lbs)	Tension (lbs)	Shear (lbs)	Tension (lbs)	Shear (lbs)
3/8 or #3	1,485	760	3,085	1,585	2,565	1,315	2,655	1,320
1/2 or #4	2,725	1,395	5,655	2,900	4,685	2,410	4,710	2,345
5/8 or #5	4,325	2,225	8,990	4,625	7,480	3,845	7,370	3,670
3/4 or #6	6,420	3,295	13,320	6,845	9,465	4,865	10,592	5,285
7/8 or #7	8,855	4,550	18,390	9,445	13,070	6,715	14,425	7,195
1 or #8	11,630	5,970	24,115	12,395	17,150	8,810	18,840	9,400
#9	-	-	-	-	-	-	23,845	11,890
1-1/4	18,595	9,555	38,585	19,830	27,430	14,095	-	-
#10	-	-	-	-	-	-	29,435	14,680

1. Allowable load capacities listed are calculated for the steel element type. Consideration of applying additional safety factors may be necessary depending on the application, such as life safety or overhead.
2. Allowable bond strength/concrete capacity must be checked against allowable steel strength to determine the controlling allowable load.
3. Allowable shear capacity is controlled by steel strength for the given conditions described on the previous page.



AC100+Gold®

ASD PERFORMANCE DATA





Allowable Load Capacities for Threaded Rod Installed with AC100+ Gold into Grout Filled Concrete Masonry^{1,2,3,4,5,6}

Anchor Diameter d (inch)	Minimum Embedment h_{nom} (inches)	Minimum Edge Distance (inches)	Minimum End Distance (inches)	Tension Load (pounds) Based on bond or masonry strength	Direction of Shear Loading	Shear Load (pounds) Based on bond or masonry strength	
ANCHOR INSTALLED INTO GROUTED MASONRY WALL FACES⁸							
3/8	3	3	4	735 ⁹	Any	490 ⁹	
		12	12	960 ⁹	Any	855 ⁹	
1/2	4	3	3	740	Any	455	
		4	4	985 ⁹	Any	655 ⁹	
		12	12	960	Any	1,425	
5/8	5	7-3/4 (Bed Joint)	3	935	Load to Edge	460	
		3	3	745	Any	410	
		12	12	1,095	Any	1,530	
3/4	6	7-3/4 Bed Joint)	3	1,030	Load to Edge	590	
		4	4	790	Any	630	
		12	12	1,155	Any	1,565	
3/4	6	7-3/4 (Bed Joint)	4	945	Load to Edge	565	
		ANCHOR INSTALLED INTO TOPS OF GROUTED MASONRY WALLS⁷					
		1/2	2-3/4	1-3/4	4	595 ⁹	Any
4	1-3/4		4	520	Load to Edge	190	
5/8	5	1-3/4	4	740	Load to End	295	
					Any	235	
3/4	6	2-3/4	4	1,260	Load to Edge	410	
					Load to End	490	

For SI: 1 inch = 25.4 mm, 1 psi = 6.89 kPa, 1 lbf = 4.45 N.

1. Tabulated load values are for anchors installed in nominal 8-inch-wide (203 mm) Grade N, Type II, lightweight, medium-weight or normal-weight grout-filled concrete masonry units conforming to ASTM C 90. If the specified compressive strength of the masonry, f'_m , is 2,000 psi (13.8 MPa) minimum the tabulated values may be increased by 4 percent.
2. The tabulated allowable loads are permitted to be increased for wind and seismic by 33-1/3 percent.
3. Allowable bond or masonry strength in tension and shear are calculated using a safety factor of 5.0 and must be checked against the allowable tension and shear load capacities for threaded rod based on steel strength to determine the controlling factor.
4. The AC100+ Gold adhesive experiences a reduction in tensile and shear capacity with increased concrete temperature. Reduction factors must be applied to the allowable values based on bond or masonry strength noted in the table when the anchors are installed in locations where the in-service concrete temperature may be greater than 75°F (24°C).
5. Anchors may be installed in the grouted cells, cell webs and bed joints not closer than 1-inch from head joints.
6. The tabulated values are applicable for anchors installed into grouted masonry wall faces and masonry wall tops at a critical spacing distance, s_{cr} , between anchors of 3 times the embedment depth.
7. Anchor installations into tops of grouted masonry walls are limited to one per masonry cell.
8. The critical spacing for use with the anchor values shown in this table is 16 anchor diameters. For 1/2 -, 5/8 - and 3/4 - inch diameter anchors, the spacing may be reduced to a minimum of 8 anchor diameters when using a tension reduction factor of 0.85 and a shear reduction factor of 0.45. Linear interpolation may be used for spacing distances between the minimum and critical distances.
9. Tabulated load values also apply to anchors installed in nominal 6-inch-wide (152 mm) Grade N, Type II, lightweight, medium-weight or normal-weight grout-filled concrete masonry units conforming to ASTM C 90. These tabulated load values may not be increased for wind and seismic.



ASD PERFORMANCE DATA



Ultimate Load Capacities for Threaded Rod Installed with AC100+ Gold Into Hollow Concrete Masonry Walls with Stainless Steel and Plastic Screen Tubes^{1,2,3}

Rod Diameter <i>d</i> in. (mm)	Minimum Screen Tube Length in. (mm)	Minimum End Distance in. (mm)	Minimum Edge Distance in. (mm)	Ultimate Load		Allowable Load	
				Tension lbs. (kN)	Shear lbs. (kN)	Tension lbs. (kN)	Shear lbs. (kN)
3/8 (9.5)	2-3/4 (69.9)	12 (304.8)	12 (304.8)	1,600 (7.2)	3,530 (15.7)	320 (1.4)	705 (3.1)
	3-1/2 (88.9)	3-3/4 (95.2)	3-3/4 (95.2)	1,600 (7.2)	1,700 (7.6)	320 (1.4)	340 (1.5)
1/2 (12.7)	3-1/2 (88.9)	3-3/4 (95.2)	3-3/4 (95.2)	2,165 (9.6)	1,700 (7.6)	430 (1.9)	340 (1.5)
	3-1/2 (88.9)	12 (304.8)	12 (304.8)	2,165 (9.6)	4,710 (21.0)	430 (1.9)	940 (4.2)
5/8 (15.9)	4-1/2 (114.3)	3-3/4 (95.3)	3-3/4 (95.3)	2,735 (12.2)	-	550 (2.4)	-

1. Tabulated load values are for anchors installed in minimum 8" wide, Grade N, Type II, lightweight, medium-weight or normal-weight concrete masonry units conforming to ASTM C 90 that have reached a designated ultimate compressive strength at the time of installation ($f'm \geq 1,500$ psi). Mortar must be type N, S or M.
2. Allowable loads are calculated using an applied safety factor of 5.0. Consideration of safety factors of 10 or higher may be necessary depending on the application, such as life safety.
3. Anchor spacing is limited to one anchor per masonry cell.

Ultimate Load Capacities for Threaded Rod Installed with AC100+ Gold into the Face of Brick Masonry Walls^{1,2}

Rod Diameter <i>d</i> in. (mm)	Drill Diameter <i>d</i> _{bit} in. (in.)	Minimum Embedment Depth in. (mm)	Minimum End Distance in. (mm)	Minimum Edge Distance in. (mm)	Minimum Spacing in. (mm)	Ultimate Load		Allowable Load	
						Tension lbs. (kN)	Shear lbs. (kN)	Tension lbs. (kN)	Shear lbs. (kN)
3/8 (9.5)	1/2	3-1/2 (88.9)	6 (152.4)	6 (152.4)	6 (152.4)	5,845 (25.9)	4,580 (20.4)	1,170 (5.2)	915 (4.1)
1/2 (12.7)	5/8	6 (152.4)	8 (203.2)	8 (203.2)	8 (203.2)	11,500 (51.2)	9,300 (41.4)	2,300 (10.3)	1,860 (8.3)


1. Tabulated load values are for anchors installed in minimum 2 wythe, Grade SW, solid clay brick masonry conforming to ASTM C 62. Mortar must be N, S or M.
2. Allowable loads are calculated using all applied safety factor or 5.0. Consideration of safety factors of 10 or higher may be necessary depending on the application, such as life safety.

Adhesive DOT Listing

State	AC100+ Gold	PE1000+	Pure 50+	Pure 110+
Alabama	Approved	Approved	Approved	Submitted
Alaska	Project by Project	Project by Project	Project by Project	Project by Project
Arizona	Submitted	Approved	Submitted	Submitted
Arkansas	Approved	Approved	Approved	Submitted
California	-	-	-	-
Colorado	Approved	Approved	Approved	Approved
Connecticut	Approved	Approved	Submitted	Submitted
Delaware	Project by Project	Project by Project	Project by Project	Project by Project
Florida	-	-	Approved	Approved
Georgia	No Criteria	Approved	Approved	Approved
Hawaii	Project by Project	Project by Project	Project by Project	Project by Project
Idaho	Project by Project	Project by Project	Project by Project	Project by Project
Illinois	Approved	-	-	-
Indiana	Approved	Approved	Approved	Approved
Iowa	Approved	Approved	Approved	Approved
Kansas	Approved	Approved	Approved	Approved
Kentucky	Approved	Approved	Submitted	Submitted
Louisiana	Approved	Approved	Approved	Approved
Maine	Approved	Approved	Approved	Approved
Maryland	-	-	Approved	Submitted
Massachusetts	-	-	-	-
Michigan	Approved	-	Submitted	-
Minnesota	Approved	Approved	Approved	Submitted
Mississippi	Approved	-	-	-
Missouri	Approved	Approved	Approved	Approved

State	AC100+ Gold	PE1000+	Pure 50+	Pure 110+
Montana	Project by Project	Project by Project	Project by Project	Project by Project
Nebraska	-	Approved	Approved	Submitted
Nevada	-	Approved	Submitted	Submitted
New Hampshire	Project by Project	Project by Project	Project by Project	Project by Project
New Jersey	Approved	Approved	Approved	Approved
New Mexico	-	Approved	Submitted	Submitted
New York	Approved	Approved	Approved	Approved
North Carolina	-	-	Approved	Approved
North Dakota	Project by Project	Project by Project	Project by Project	Project by Project
Ohio	Approved	Approved	-	-
Oklahoma	Project by Project	Project by Project	Project by Project	Project by Project
Oregon	-	Approved	Submitted	Submitted
Pennsylvania	-	-	-	-
Rhode Island	Approved	Approved	Submitted	Submitted
South Carolina	Project by Project	Project by Project	Project by Project	Project by Project
South Dakota	Project by Project	Project by Project	Project by Project	Project by Project
Tennessee	Approved	Approved	Approved	Approved
Texas	-	Approved	Approved	Approved
Utah	Approved	Approved	Approved	Submitted
Vermont	-	-	Approved	Submitted
Virginia	Approved	Approved	Submitted	Submitted
Washington	Approved	Approved	-	-
West Virginia	Project by Project	Project by Project	Project by Project	Project by Project
Wisconsin	Approved	No Criteria	No Criteria	No Criteria
Wyoming	Project by Project	Project by Project	Project by Project	Project by Project

AC100+Gold State DOT Listing Map



PRODUCT SUBMITTAL / SUBSTITUTION REQUEST

TO:

PROJECT:

SPECIFIED ITEM:

Section	Page	Paragraph	Description
---------	------	-----------	-------------

PRODUCT SUBMITTAL / SUBSTITUTION REQUESTED:

The attached submittal package includes the product description, specifications, drawings, and performance data for use in the evaluation of the request.

SUBMITTED BY:

Name:

Signature:

Company:

Address:

Date:

Telephone:

Fax:

FOR USE BY THE ARCHITECT AND/OR ENGINEER

Approved **Approved as Noted** **Not Approved**

(If not approved, please briefly explain why the product was not accepted.)

By:

Date:

Remarks:

POWERS FASTENERS BRANCH INFORMATION

NATIONAL ACCOUNT SPECIALIST

ELLEN BAUM

312-202-2747

USA LOCATIONS

CITY	ADDRESS	PHONE	FAX
Alabama	5405 Buford Hwy Suite 410 Norcross, GA 30071-3984	678-966-0000	678-966-9242
Atlanta	5405 Buford Hwy Suite 410 Norcross, GA 30071-3984	678-966-0000	678-966-9242
Boston	2 Powers Lane, Brewster, NY 10509	800-524-3244	877-871-1965
Charlotte	349 L West Tremont Avenue, Charlotte, NC 28203	704-375-5012	704-376-5517
Chicago	2472 Wisconsin Avenue, Downers Grove, IL 60515	630-960-3156	630-960-3912
Dallas	1300 IH 35 North, Suite #118, Carrollton TX 75006	972-446-5985	972-446-3674
Denver	2475 West Second Street #35, Denver, CO 80223	303-922-9202	303-922-9228
Detroit	21600 Wyoming Avenue, Oak Park, MI 48237	248-543-8600	248-543-8601
Florida	2412 Lynx Lane, Orlando, FL 32804	813-626-4500	813-626-4545
Houston	13833 North Promenade, Suite 100, Stafford, TX 77477	281-491-0351	281-491-0367
Indianapolis	15290 Stony Creek Way, Noblesville, IN 46060	317-773-1668	317-773-1690
Los Angeles	2761 Dow Avenue, Tustin, CA 92780	714-731-2500	714-731-2566
Maryland	3137-B Pennsy Drive, Landover, MD 20785	301-773-1722	301-341-5119
Milwaukee	12020 W. Feerick Street, Milwaukee, WI 53222	414-466-2400	414-466-3993
Minneapolis	351 Wilson Street, NE Minneapolis, MN 55413	612-331-3770	612-331-3549
Missouri	3225 Harvester Road, Kansas City, KS 66115	816-472-5033	816-472-5040
New Orleans	102 Sampson Street, Houston, TX 77003	713-228-1524	713-228-1528
New York	2 Powers Lane, Brewster, NY 10509	800-524-3244	877-871-1965
Philadelphia	2 Powers Lane, Brewster, NY 10509	800-524-3244	877-871-1965
Phoenix	3602 E. Southern Ave, Suite 5 Phoenix, AZ 85040	602-431-8024	602-431-8027
Pittsburgh	1360 Island Avenue, McKees Rocks, PA 15136	412-771-3010	412-771-9858
Portland	14221 NE 190th St., Suite 125, Woodinville, WA 98072	714-731-2500	714-731-2566
Rochester	36 Van Auker Blvd., Rochester, NY 14608	800-524-3244 / 585-529-4188	877-871-1965 / 585-529-5319
Salt Lake City	3120 W. California Ave, Suite E, Salt Lake City, UT 84104	801-466-9428	801-466-3083
San Francisco	28970 Hopkins Street, Suite B+C, Hayward, CA 94545	510-293-1500	510-293-1505
Seattle	14221 NE 190th St., Suite 125, Woodinville, WA 98072	714-731-2500	714-731-2566
Tennessee	221 Blanton Avenue, Nashville, TN 37210	615-248-2667	615-248-2676

INTERNATIONAL LOCATIONS

COUNTRY/REGION	ADDRESS	PHONE	FAX
Australia	Factory 3, 205 Abbotts Road, Dandenong, South Victoria 3175	+61 3 8787 5888	+61 3 8787 5899
Canada	6275 Millcreek Drive, Mississauga, Ontario L5N 7K6	1-800-567-7188	1-800-265-9680
China	8/F, Lujiazui Fund Tower, No. 101, Zhu Lin Road, PuDong District, Shanghai, China 200122	+86-21-6162-1858*2234	+86-21-5080-5101
Europe	Westrak 208, 1771 SV Wieringerwerf, Netherlands	+31 888 769 377	+31 227 594 759
Manitoba	1810 Dublin Avenue Man. Winnipeg, R3H 0H3	204-633-0064	204-694-1261
New Zealand	PO Box 302 076 North Harbour Auckland	+64 9415 2425	+64 9415 2627
Quebec	721 Meloche Avenue, Dorval, Quebec H9P 2S5	514-631-4216	514-631-2583

LATIN & CARIBBEAN DISTRIBUTION INQUIRIES

COUNTRY/REGION	ADDRESS	CONTACT	PHONE	FAX
Latin America		Allan Herbert	0050767477749	877-871-1965

LATIN & CARIBBEAN DISTRIBUTION

COUNTRY/REGION	ADDRESS	CONTACT	PHONE	FAX
Brazil	HARD, Rua Dr. Humberto Pinheiro Viera, 150 Lote B, 1 B Distrito Industrial, Joinville, Brazil		55-47-40097209	55-47-40097217
Colombia	Electrogeno, S.A., Carrera 52 #71c-38, Bogota, Colombia		(57) 1 6600 9436	
Costa Rica	Tecnofijaciones de Costa Rica,, La Uruca, costado Este del Banco Nacional, Condominio Horizontal JW, Bodega #21, San Jose, Costa Rica	alguerak@tecnofijacionescr.com	00-506-2256-8115/8117	00-506-2256-8149
	Cel Internacional s.a., Alajuela, Costa Rica, Apartado 674-4050	ventas@celcr.com	00-506-2432 5868	00-506-2440-1839
Dominican Republic	Calle Estancia Nueva #17 E Esquina Cul-De-Sac 9, San Geronimo, Santo Domingo	Rodfor Team	809-224-5615	809-472-8640
Ecuador	Acero Comercial Ecuatoriano S.A., Av. La Prensa N45-14 y Telégrafo 1 – Quito	info@acero.comercial.com	(593-2) 2454 333	(593-2) 2454 455
	Av. Juan Tanca Marengo Km. 1.7 – Guayaquil	infogy@acero.comercial.com	(593-4) 2683 060	(593-4) 2683 059
Guatemala	Multimateriales s.a., 1 calle, #33-88, Zona 1, Colonia Toledo, Guatemala 01011	info@multimateriales.com	00-502-2429-6700	00-502-2429-6767
Mexico	Multiaccesorios, Av.A tiempo, #502, Parque, Nuevo Leon	jnlazo@multiaccesorios.com	00-52-81-8042-4200	00-52-81-1231-0048
	Fulminantes Industriales, Encino No.1103, Col Granjas, Chihuahua	irmafp@live.com	00-52-614-419-0090	00-52-614-419-8523
	Sergio Paulo Ramirez, Colonia Jardines de Jerez, Gardenias #103, Leon, Guanajuato	prosetgto@hotmail.com	00-52-477-711-0670	00-52-477-212-2478
Panama	Centro-Industrial, Via Cincuentenario, No. 7910, Ciudad Panama, Panama		(507) 302-8022	
	Meca, Via Argentina #46-70, Edif. Rattan, Planta Baja Local 5, Panama	rvanselow@germantecpa.com	00-507-269-4333	00-507-269-1866
	Fixa Panama, Via Porras, Edif. 54, Local #7, San Francisco	ventas@fixapanama.com	00-507-260-9505	
Peru	Powers Peruana SAC, Av. Santa Catalina, 571 La Victoria, Lima 13, Peru (www.powersperuana.com)	Martin Vasquez	00 511 265 8500	00 511 330 0909
Venezuela	Andajes Powers s.a., Calle Sucre/Qta. Maudora, #1721 Entre Cec Acosta Y San Ignacio Chacao, Caracas	Distributor andajespowers@hotmail.com	58 212 264 1313	58 212 263 0219
Trinidad - Tobago	Ft. Farfan, 3-5 Ibis Avenue, Ibis Acres, San Juan	Derek Cumming	(868) 674-7896	

Note: The information and data contained within this documentation was current as of April 2014. The information is for marketing purposes only and is subject to change and updates as needed. Powers Fasteners, Inc. reserves the right to change designs and specifications without notice or liability for such changes. Please contact Powers Fasteners for the most current and up to date available information or refer to our website at www.powers.com

Powers Fasteners 701 E. Joppa Road, Towson, MD 21286 P: (800) 524-3244 F:(877) 871-1965

www.powers.com

Cat. No. 49149 4/14

©2014 Powers Fasteners, Inc.

